# **APEX TITAN PROTECT HT-EP SERIES**

**High Temperature Clay based - Extreme Pressure Greases** 



## **Product Data Sheet**

#### **Product Description**

APEX TITAN PROTECT HT-EP series are high temperature greases, formulated with bentonite clay based thickener and extreme pressure additive system to provide extra protection against wear, rusting and water washout especially in industrial equipment operating under heavy loads and high temperatures. They are available in NLGI grades ranging from 00 to 3 with base oil viscosity of ISO VG 150 & 320. It retains its consistency at high temperatures and provides good storage stability.

## **Features & Benefits**

- Outstanding Non-melting capability protects bearing at very high operating temperatures where conventional soap-based greases fail to provide satisfactory lubrication.
- Good extreme pressure & anti-wear properties protects bearing surfaces against severe wear, even under high load conditions.
- Excellent Oxidation and Thermal stability protects against deposit formation at very high operating temperatures, thus maintains the life and performance of grease.
- Excellent resistance to water washout resists washout of grease in equipment and provides good lubrication even in presence of water.
- Excellent retention of consistency resists grease softening in application, where very hightemperatures and mechanical working leads to subsequent loss of lubrication performance and leakage.

#### **Application**

#### APEX TITAN PROTECT HT-EP series are suitable for below applications:

- Drying Ovens
- Jaw Crushers
- Kiln cars
- · Steel Mills
- Hot Rolling Mills
- · Aluminum, Cement, Glass and Rubber plants

## **Typical Characteristics**

Apex Titan Grease	Test Method	Units	НТ-ЕРОО	HT-EP0	HT-EP1	HT-EP2	НТ-ЕРЗ
NLGI Grade	ASTM D 217		0	0	1	2	3
Thickener Type			Bentonite Clay	Bentonite Clay	Bentonite Clay	Bentonite Clay	Bentonite Clay
Penetration, Worked @ 25 <sup>0</sup> C	ASTM D 217	0.1mm	400-430	355-385	310-340	265-295	220-250
Viscosity @ 40 °C	ASTM D 445	cSt	32	160	160	160	160
Dropping Point	ASTM D 566	°C	-	03>	03>	03>	03>
4-Ball Wear, Scar	ASTM D 2266	mm	0.5	4.0	4.0	4.0	4.0
4 Ball Weld Load	ASTM D 2596	Kg	42	52	52	52	52

The above figures are typical of blends with normal production tolerance and do not constitute a specification.